Original Article

Studying Synthesis of Modifier Based on Croton Aldehyde and Phthalimine and Sulfur Modified Bitumen BH 90/30

M.S. Rosilov¹, Kh.S. Beknazarov², J.R. Chuliev³, Sh.U. Babadjanova⁴

^{1,3} Department of Chemical Technology, Karshi Engineering and Economic Institute, Karshi, Uzbekistan.

²Doctor of Technical Sciences, Angreen University, Tashkent, Uzbekistan.

⁴Department of Pathological Anatomy, Forensic Medicine, Medical Law Termez branch of Tashkent Medical Academy,

Termez, Uzbekistan.

¹Corresponding Author : abrornomozov055@gmail.com

Received: 04 November 2024Revised: 21 January 2025Accepted: 01 March 2025Published: 26 April 2025

Abstract - In this paper, the optimal conditions for synthesising a modifier with a new composition for bitumen modification were studied. For the synthesis of this modifier, the initial croton aldehyde was obtained from substances such as aldehyde and phthalimine in a 1:1 mol ratio, and the temperature was kept below 5°C. To determine the chemical structure of this synthesized compound, the chemical formula of the new structural modifier was proposed using modern methods such as IR-spectroscopy, NMR and PMR. First, this modifier interacted with sulfur, and then BN 90/30 brand bitumen was used to prepare modified bitumens. Different masses were mixed in a heat-resistant 1000 ml container at various mixing speeds and temperatures, specifically 135, 140, 145, and 160°C. According to the results obtained, the reaction yield of bitumen was modified at the optimal temperature of 160°C and a high 94.8%. Modified bitumen's composition and physicochemical and mechanical properties have been thoroughly studied using modern analytical methods. Infrared spectroscopy analysis methods determined its structure and composition. The surface morphology and element content were analyzed in tabular form using an MIRA 2 LMU scanning electron microscope. Heat resistance and destruction of modified bitumen were studied using thermogravimetric (TG) and differential thermal analysis (DTA) methods. Based on the results of this analysis, it is recommended that modified bitumen be used in asphalt roads, roofing and waterproofing materials.

Keywords - Modifier, Croton aldehyde, Phthalimine, BN 90/30 brand bitumen, NMR and PMR.

1. Introduction

Currently, the oil refining industry is developing a wide range of high-quality bitumen products obtained as a result of the distillation process[1,2]. These bitumen products are widely used in producing inexpensive and effective waterproofing and building materials and are effectively used in repair and moisture insulation works[3]. These petroleumbased bitumens formed during the distillation process are used as the main moisture barrier raw material [4].

Bitumen obtained based on oil has high hydro-, electricaland thermal insulation properties and is a material resistant to chemical substances, radiation and atmospheric effects[5]. Therefore, they are widely used in electrochemistry, chemical industry, nuclear power and agriculture. In recent years, the demand for the use of polymer-based additives to improve the quality of bitumen has been increasing. In the modification of bitumen, polar groups present in polymer molecules are mainly carried out by reacting with polar components of bitumen [6]. It prevents the separation of phases and increases the strength of materials obtained based on modified bitumen [7]. The amount of tripolymers and sulfur used in bitumen modification must have clearly defined high-quality indicators so that the chemical composition of the main network does not reach the gel state. According to research, this amount can usually be 5-5.5% by weight, but in some cases, less than 1% has been found to be effective[8]. In addition, in some sources, higher results were recorded for bitumen samples with lower amounts of tripolymer and sulfur. Therefore, adding an excess amount of tripolymer is considered a cost-effectiveness factor[9].

2. Materials

BN 90/30 brand bitumen is produced in Uzbekistan "Karshi Oil Refinery". Sulfur, were croton aldehyde, and phthalimine were used for this study also, and they were purchased as "chemically pure" from the "Merit Chemicals" company in Uzbekistan.

2.1. Methods

2.1.1. IR Analysis

The SHIMADZU IR-Fure spectrophotometer, made in Japan, was used to investigate the infrared spectra of the sulfur-modified bitumen at 400 and 4500 cm⁻¹. The analysis based on the IR spectrum.

2.1.2. SEM-EDX-Analysis

The images of the surface of the sulfur-modified bitumen obtained in different sizes were taken on a JSM-IT200 device with elemental dispersion analysis (SEM - EDX) belonging to the Japanese company JEOL.

2.1.3. TGA and DTA Analysis

Thermogravimetric studies of changes in the physicochemical properties of the obtained sulfur-modified bitumen under the influence of temperature were studied on the DTG-60 device, SHIMADZU (Japan). Analytical conditions: in an argon atmosphere (80 mi/min), the rate of temperature increase was -10C/min.

2.1.4. Quantum Chemical Analysis

Quantum-chemical calculation of the reactivity of the corrosion inhibitor molecule using Avogadro, Hyper Chem 8.01, Asselrys MS Modeling 3.0.1 using the constrained Semi-empirical (DFT) method, semi-empirical AM1, MNDO, PM3, RM1 and MINDO3 using SCF-MO calculations were carried out using the Intel Pro Pentium 1.40 GHz computer.

2.1.5. Bitumen Mixing Machine

For mixing, Model- ELR401/3, Power (kW)- 1.1/1.5, Rotation speed- 3000(rpm), Flow-0.5 (m³/h), Inlet-DN40(mm) and outlet DN32(mm) were used.

2.1.6. Synthesis of the Modifier

0.5 mol of croton aldehyde and 1 mol of phthalamine are added to a 250 ml round-bottomed flask filled with ice water and mixed for two hours after cooling. The solution is evaporated in a porcelain container, and the volume is brought up to 100 ml. Then, the resulting modifier is filtered (Scheme 1).



2-Scheme. Modification of sulfur with a modifier

2.2. IR Analysis



To determine the structure of the modifier, IR-spectroscopy analysis was carried out. The IR spectrum of the modifier is depicted in Figure 1, in which the CO-NH₂ bonds characteristic of amide groups are clearly observed in the bands of 3498, 700 and 650 cm^{-1} .

Absorptions corresponding to -C-N bonds in amide groups were recorded at 1614 and 1269 cm⁻¹. Bonds specific to the benzene ring were detected at 1597 and 1570 cm⁻¹, while C–H bonds in the benzene ring were recorded at 1070, 862, 810, 752 and 719 cm⁻¹. Also, absorption wavelengths corresponding to C–O bonds were observed in the 1348 and 1294 cm⁻¹ bands[10,11].

2.3. NMR and PMR

In addition, the study and analysis of the structure of these synthesized modifiers were also studied with the help of NMR and PMR spectra.



Fig. 2 ¹H NMR spectrum analysis of the modifier

In the NMR-spectrum of the modifier was analyzed, the proton signals in the benzene ring (H -3 and H-4) were quintet resonance at 7.392-7.386 m.u., (H -5) was triplet resonance at 6.996-6.990 m.u., (H -6) was 7.9 m.u. Doublet resonance at (N-9) 8,408-8,390 m.u. Doublet resonance at (H -10) 6,129-6.041 m.u. Triplet resonance at (H -11), multiplet resonance at 6,149-6,132 m.u., and (H -12) doublet resonance signals at 1,938-1,922 m.u.





In the ¹³C NMR spectrum of the modifier, the 1st carbon in the carboxyl group is 118.957 m.u., the 2nd carbon is 147.155 m.u., the 3rd carbon is 128.777 m.u., the 4th carbon is 134.595 m.u., the 5th carbon is 126.355 m.u glerod 133.004 m.u., carboxyl carbon in group 170.421 m.u., carbon in -N=CH- (C-9) 159.596 m.u., carbons C-10 and C-11 connected with a double bond are 130.601 and 137.756 m.u., and carbon in methyl group is 18.038 m.u. showed the relevant signals. The resulting spectrum confirms the structure of the synthesized substance[12, 13].

2.3.1. Analysis of Modifier Reactivity with Sulfur using Quantum Chemical Method

The process of studying the "composition-structureproperty" system in chemical compounds allows us to theoretically estimate the properties, composition and molecular structure of compounds. This information helps in the synthesis of compounds with selected properties.

In order to determine the reaction properties of the modifier molecule, quantum chemical calculations were performed using semi-empirical AM1, MNDO, PM3, RM1 and MNDO3 methods in Avogadro, Hyper Chem 8.01 and Asselrys MS Modeling 3.0.1 programs. Molecular geometry optimization was performed using the Polak-Ribiere (Conjugate Gradient) algorithm.

M.S. Rosilov et al. / IJETT, 73(4), 34-43, 2025



and it bittent contraction of action at the second of the	able	1. Effe	ective	charge	distribution	ı on da	onor atoms	of m	odifier	molecules
---	------	---------	--------	--------	--------------	---------	------------	------	---------	-----------

Table 2 Effective	charge value	es of donor	atoms in m	difier molecules
I able 2. Effective	Charge value	cs of uonor	atoms in m	Junier molecules

Atoms	AM1, eV	MNDO, eV	PM3, eV	RM1, eV	MNDO3, eV
			XXX		
$\delta_q S^1_{(-S-)}$	-0,118	0,045	-0,006	-0,032	-0,209
$\delta_q S^2_{(-S-)}$	0,066	-0,024	0,053	0,003	0,060
$\delta_q S^3_{(-S-)}$	0,084	-0,012	0,039	-0,024	-0,078
$\delta_q S^4_{(-S-)}$	-0,150	-0,013	-0,078	-0,048	0,004
$\delta_q S^{5}_{(-S-)}$	-0,019	0,006	-0,013	0,022	0,100
$\delta_q S^6_{(-S-)}$	-0,070	-0,018	-0,047	-0,052	-0,103
$\delta_q S^{7}_{(-S-)}$	-0,154	-0,031	-0,048	-0,174	0,035
$\delta_q S^8_{(-S-)}$	0,463	0,234	0,108	0,436	-0,038
$\delta_q N^1_{(NH)}$	-0,507	-0,474	-0,168	-0,615	-0,080
$\delta_q O^1_{(C=O)}$	-0,295	-0,312	-0,320	-0,300	-0,467
$\delta_q O^1_{(C=O)}$	-0,313	-0,308	-0,325	-0,298	-0,574
$\delta_q N^1_{(\text{-}N=)}$	-0,270	-0,346	-0,219	-0,480	-0,291
$\delta_q S^9_{(-S-)}$	0,002	0,043	-0,066	0,198	-0,150
$\delta_q S^{10}_{(-S-)}$	-0,079	-0,002	0,019	-0,084	-0,053
$\delta_q S^{11}_{(-S-)}$	0,087	-0,017	0,092	-0,060	-0,079
$\delta_q S^{12}_{(-S-)}$	0,045	-0,019	-0,026	-0,046	0,406
$\delta_q S^{13}_{(-S-)}$	-0,165	-0,007	-0,116	0,021	-0,230

$\delta_q S^{14}_{(-S-)}$	0,012	-0,006	0,015	-0,050	0,060
$\delta_q S^{15}_{(-S-)}$	0,096	-0,030	0,056	0,002	0,160
$\delta_q S^{16}_{(-S-)}$	0,030	0,031	-0,034	0.023	-0,315
$\delta_q N^2_{(NH)}$	-0,247	-0,346	-0,192	-0,407	-0,252
$\delta_q O^1_{(C=O)}$	-0,310	-0,292	-0,310	-0,310	-0,558
$\delta_q O^1_{(C=O)}$	-0,350	-0,326	-0,352	-0,365	-0,546
$\delta_q N^2_{(-N=)}$	-0,410	-0,324	0,002	-0,509	-0,240
E	-7236,2244 (kcal/mol)	-7224,9711 (kcal/mol)	-7264,9073 (kcal/mol)	-3939,1605 (kcal/mol)	-7428,9709 (kcal/mol)

According to Mulliken's method, the obtained results show high values of negative effective charge in modification molecules shown in oxygen atoms of C=O and C-O-C groups and nitrogen atoms of N-H groups[14, 15]. The geometric optimization of the modifier was performed using the Avogadro program and was performed using the RHF/6-311G(d,p) basis set in GaussView 6.0.16. Charges were calculated using the DFT (B3LYP) method and the Mulliken method.

Charge distribution is important in determining a molecule's electrophilic and nucleophilic centers. A high negative charge is localized on nitrogen and oxygen atoms in the modifier molecule (Figure 4b). Electron density in frontier molecular orbitals (ChegMOs) plays an important role in evaluating the reactivity of organic compounds. The higher occupied molecular orbital (LUMO) is recognized as an electron donor, and the Lower Unoccupied Molecular Orbital (LUMO) as an electron acceptor[16].



Fig. 4 Effective charge distribution on donor atoms in modifier molecules

According to the charge density of the higher occupied molecular orbital (HOMO) and lower unoccupied molecular orbital (LUMO), the largest distribution of charge density belongs to the -O-, C=O and N-H groups (Figure 4c,d). HOMO and LUMO orbital energies and the difference between them (DE=E_{LUMO}-E_{HOMO}, eV) are also important. An increase in the HOMO energy (increasing the occupied level towards the LUMO) in a series of compounds indicates an increase in the electron-donating property of the compound. The LUMO energy determines the electron acceptor ability (propensity for electrons) of compounds. Ionization potential, I=- E_{HOMO} , (eV), Electron propensity, A=- E_{LUMO} , (eV), Electronegativity, $\chi = (I + A)/2$ (eV), Chemical hardness, $\eta =$ (I - A) /2 (eV), Chemical potential, μ_p =-(I + A)/2 (eV), Chemical softness, $\sigma = 1/(2\eta)$ (eV-1), Electrophilicity index, $\omega = \mu_p^2/2\eta$ (eV), dipole moment, μ (Debay) was calculated. The results are presented in Table 3.

Quantum-Chemical Parameters	Modification
E _{HOMO} , eV	-9,74
E _{QBMO} , eV	-0,32
$ \Delta E = E_{QBMO} - E_{HOMO}$ (eV)	9,43
Ionlanish potensiali, I=- E _{HOMO} , (eV)	9,74
Elektronga moyillik, A=-E _{QBMO} , (eV)	0,32
Elektromanfiylik, $\chi = (I + A)/2$ (eV)	5,03
Kimyoviy qattiqlik, $\eta = (I - A)/2$ (eV)	4,71

Kimyoviy potensial, μ_p =-(I + A)/2 (eV)	-5,03
Kimyoviy yumshoqlik, $\sigma = 1/(2\eta)$ (eV-1)	0,11
Elektrofillik indeksi, $\omega = \mu_p^2/2\eta$ (eV)	2,68
Dipol moment, µ (Debay)	6,67

It is known that the level of electrostatic potential is used to determine the electron donor and electron acceptor parts of a molecule. MEP (molecular electrostatic potential) plots in red, blue, and green are negative, positive, and neutral electrostatic potentials, respectively (Figure 5). Due to the high splitting energy in the orbital of this modifier, it forms compounds with sulfur.



Fig. 5 ESP-HOMO (a), ESP-LUMO (b) and ESP(c,d) of the modifier

3. Results and Discussion

3.1. Modification of Bitumen with a Modifier

Sulfur was modified with the originally synthesized modifier. In this case, the modifier was added in the amount of 2% by weight of sulfur. This process helps improve sulfur's properties and obtain a modified material. BND 60/90 bitumen must be heated until it becomes anhydrous at a temperature not exceeding 160 °C. If the temperature exceeds 160 °C, the binding properties of bitumen may be lost. After the bitumen is fully heated, it is mixed with modified sulfur. In this process, bitumen should be poured over modified sulfur, and the mixture should be stirred for 30-40 minutes. Modified sulfur and bitumen enter into a chemical reaction and the physicochemical properties of bitumen change. The optimal ratio is to mix sulfur and bitumen in a 20-80% ratio. If the sulfur content of cerobitum exceeds or decreases by 10%, the viscosity and plasticity decrease, and the cerobitum produced does not meet standard requirements[17]. Considering the above, 600 g of bitumen was placed in a container and heated until it liquefied at a temperature of 130-160 °C. 160 g of modified sulfur (3.2 g of modifier) should not be added to diluted bitumen at a speed of 150-200 ylan/minute because if this norm is exceeded, the quality indicators of sulfur-bitumen may change negatively. The modification process is carried out at a temperature of 200°C for 2 hours. The most optimal conditions for the production of modified bitumen were studied, and the physico-chemical properties of the bitumen were analyzed. According to the research results, the composition of bitumen with the highest efficiency was determined. This optimal composition has properties that help to increase the performance of modified bitumen, improve the workability of bitumen and make it suitable for various construction works[18-22]. Modified bitumen was tested under different conditions and ratios. The modified bitumen obtained as a result of the research was calculated depending on the temperature and mass ratio of the components. The highest reaction temperature was 160 °C, and the highest yield was obtained from the modified bitumen with a ratio of 80:19.6:0.4 (Figure 6).

No	B:S:M	T,⁰C	Reaction yield ω,%	No	B:S:M	T,⁰C	Reaction yield ω,%
1		125	38.2	1		125	25.3
2	80.10.0 2	135	43.6	2	80.10 5.0 5	135	48.4
3	00:19:0.5	145	69.8	3	00:19,5:0.5	145	68.7
4		160	76.4	4		160	76.8
No	B:S:M	T,⁰C	Reaction yield ω,%	No	B:S:M	T,⁰C	Reaction yield ω,%
No 1	B:S:M	T,°C 125	Reaction yield ω,% 25.3	No	B:S:M	T,°C 125	Reaction yield ω,% 25.3
No 1 2	B:S:M	T,°C 125 135	Reaction yield ω,% 25.3 61.2	No	B:S:M	T,°C 125 135	Reaction yield ω,% 25.3 68.4
No 1 2 3	B:S:M 80:19,7:0.3	T,°C 125 135 145	Reaction yield ω,% 25.3 61.2 75.8	No	B:S:M 80:19,6:0,4	T,°C 125 135 145	Reaction yield ω,% 25.3 68.4 84.8

Table 4 Effect of modification on product	vield temperature and ratio of	starting materials (hitumen)	(B) sulfur (S) modifier in %)
1 able 4. Effect of mounication on product	yield, temperature and rado or	starting materials (bitumen	(D), summer (S), mounter in 70)



Fig. 6 The effect of the amount of starting materials and temperature on the reaction yield of bitumen

3.2. IR Analysis

Based on the IR spectrum analysis, we can see the structure of bitumen modified with sulfur, which has the following structure (Figure 7). In the area of 2902.87 cm⁻¹, groups caused by asymmetric and symmetric valence vibrations of methyl (-CH₃) and methylene (-CH₂) groups are located. In the region of 1039.63 cm⁻¹, the vibration of the sulfo bond of the S-S group can be seen. -C=C- bonds in 1653 cm⁻¹ area, -C-S-C- valence vibrations in 1064.71 cm⁻¹ area, as well as NH-S bonds belonging to amide groups in 777.31 cm⁻¹ and 877.61 cm⁻¹ areas we can see from Figure 7.



Fig. 7 The IR spectrum of modified bitumen

3.3. SEM and Elemental Analysis of Modified Bitumen

The surface morphology and elemental composition of the modified bitumen were studied by scanning electron microscope and elemental analysis, in which the completeness of the reaction and the elemental composition of the substances formed in parallel in the reaction are presented in Figure 8.



Fig. 8 SEM and elemental analysis of modified bitumen

100 magnified images of the modified bitumen were taken, and it was proved that the substances involved in the reaction had fully reacted and changed the composition of the bitumen, that the initial substances were completely combined with each other, and that there were no additives in the composition of the substances.

3.4. Thermogravimetric (TG) and Differential Thermal Analysis (DTA)

To study the thermal properties of modified bitumen, 16,136 mg of samples were taken, and TG-DTA analysis was performed at temperatures ranging from 10°C to 802°C. In the thermal analysis results, two main endothermic effects were observed, which were recorded at temperatures of 60.87°C and 722.83°C, respectively.

The thermogravimetric (TG) curve of modified bitumen has three intensive mass loss stages. In the first stage, mass loss occurs in the temperature range from 20.39°C to 191.54°C. The second stage of mass loss is observed from 191.54°C to 458.35°C. The third and highest temperature mass loss occurs in the interval from 458.33°C to 801.65°C. These three stages of mass loss reflect different thermal stability and degradation processes of bitumen components.



Fig. 9 Thermogravimetric (TG) and Differential Thermal (DTA) analysis of modified bitumen

The thermogravimetric (TG) and differential thermal analysis (DTA) results of the modified bitumen show that 7.734% mass loss was observed in the first mass loss stage, 10.201% mass loss in the second stage and 20.352% mass loss in the third stage. DTA results of modified bitumen show energy absorption in temperature ranges from 41.24° C to

90.07°C and from 700.1°C to 750.29°C[18-21]. For a more comprehensive analysis of the TG and DTA results of this modified bitumen, detailed information is provided in Table 5. The information presented in the table helps to better understand the thermal properties of bitumen and the thermal stability of its components.

No	Temperature (°C)	Lost mass	Mass loss	The Amount of Energy	Residual mass, dw,				
110	Temperature (C)	(mg)	(%)	Consumed (µV*s/mg)	(mg)				
1	100	15,3	0,836	5,18	11,49				
2	200	14,8	1,336	8,27	19,28				
3	300	14,05	2,086	12,9	16,3				
4	400	13,5	2,636	16,3	12,8				
5	500	13,02	3,116	19,3	8,7				
6	600	12,14	3,996	24,7	-3.52				
7	700	10,7	5,436	33,68	-20.2				
8	800	9,9	6,236	38,6	-25,9				

Table 5. Thermogravimetric and differential thermal analysis of modified bitumen

4. Conclusion

As a result of this study, a new type of modifier was synthesized and modified with sulfur to modify BN 90/30 bitumen. The following can be concluded from the research results.

- When the composition of the modifier obtained based on croton aldehyde and phthalimine is studied by IR spectra, the resulting substance contains CO-NH₂ bonds characteristic of amide groups are clearly observed in the bands of 3498, 700 and 650 cm⁻¹, -C-N bonds in amide groups were recorded at 1614 and 1269 cm⁻¹, 1597 and 1570 cm⁻¹, while C-H bonds in the benzene ring were recorded at 1070, 862, 810, 752 and 719 cm⁻¹;
- The structure of the synthesized modifier was also studied using NMR and PMR analysis methods. When the NMR spectrum of the modifier was analyzed, the proton signals in the benzene ring were observed as follows:
 - H-3 and H-4 at 7.392–7.386 m.u., H-5 at 6.996– 6.990 m.u., and H-6 at 7.9 m.u. Additionally, a doublet resonance was observed at H-9 (8.408–8.390 m.u.), another doublet resonance at H-10 (6.129– 6.041 m.u.), and a triplet resonance at H-11. A multiplet resonance appeared at 6.149–6.132 m.u., and H-12 exhibited doublet resonance signals at 1.938–1.922 m.u.
- In the ¹³C NMR spectrum of the modifier, the chemical shifts were as follows:
 - The 1st carbon in the carboxyl group at 118.957 m.u., the 2nd carbon at 147.155 m.u., the 3rd carbon at 128.777 m.u., the 4th carbon at 134.595 m.u., and the 5th carbon at 126.355 m.u. Additionally, carbon at 133.004 m.u., the carboxyl carbon at 170.421 m.u., and the carbon in the -N=CH- group (C-9) at 159.596

m.u. were observed. The carbons C-10 and C-11, connected by a double bond, appeared at 130.601 and 137.756 m.u., respectively, while the carbon in the methyl group was 18.038 m.u. The resulting spectrum confirms the structure of the synthesized substance.

- The degree of bitumen modification of the compound obtained as a result of the interaction of sulfur with the modifier and determine the reaction properties of the modifier molecule, quantum chemical calculations were performed using semi-empirical AM1, MNDO, PM3, RM1 and MNDO3 methods in Avogadro, Hyper Chem 8.01 and Asselrys MS Modeling 3.0.1 programs. Molecular geometry optimization was performed using the Polak-Ribiere (Conjugate Gradient) algorithm. According to Mulliken's method, the obtained results show high values of negative effective charge in modifier molecules shown in oxygen atoms of C=O and C-O-C groups and nitrogen atoms of N-H groups;
- Optimum conditions for modifying bitumen with the synthesized modifier, such as the proportions of substances, temperature and mixing speed, were studied;
- The structure of modified bitumen was studied and analyzed using IR-spectra. In the region around 2902.87 cm⁻¹, absorption bands corresponding to the asymmetric and symmetric stretching vibrations of methyl (-CH₃) and methylene (-CH₂) groups are observed. The 1039.63 cm⁻¹ region exhibits vibrations associated with the sulfo bond (S–S group). Stretching vibrations of C=C bonds appear near 1653 cm⁻¹, while C–S–C bond vibrations are detected around 1064.71 cm⁻¹. Additionally, bands at 777.31 cm⁻¹ and 877.61 cm⁻¹ are attributed to NH–S bonds related to amide groups.

• Morphology and composition of modified bitumen were studied and analyzed using SEM and elemental analysis. Thermogravimetric (TG) and differential thermal analysis (DTA) of modified bitumen were also studied.

Funding Statement

This article was funded by Karshi Engineering and Economic Institute. Karshi, Uzbekistan.

Declaration of Competing Interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgments

The authors express their thanks to Termez State University and Termez Institute of Engineering and Technology for their support of this research work.

Authors' Contribution Statement

M.Rosulov: data curation and formal analysis. Kh.Beknazarov: investigation, methodology, and original draft. J.R Chuliev: review and editing. Ashurov J. M.: review and editing. Sh. U. Babadjanova: conceptualization, writing (original draft), and supervision. All authors have read and agreed to the published version of the manuscript.

References

- A.A. Mamedova, T.M. Naibova, and A.A. Alieva, "Composite Materials Based on Elastomer, Co-oligomer and Bitumen," *Chemistry for Sustainable Development*, vol. 32, no. 1, pp.70-75, 2024. [CrossRef] [Publisher Link]
- [2] Meng Ling et al., "Mechanistic-Empirical Models for Top-Down Cracking Initiation of Asphalt Pavements," *International Journal of Pavement Engineering*, vol. 21, no. 4, pp. 464-473, 2020. [CrossRef] [Google Scholar] [Publisher Link]
- [3] Mohammad J. Khattak, Gilbert Y. Baladi, and Lawrence T. Drzal, "Low Temperature Binder-Aggregate Adhesion and Mechanistic Characteristics of Polymer Modified Asphalt Mixtures," *Journal of Materials in Civil Engineering*, vol. 19, no. 5, pp. 411-422, 2007. [CrossRef] [Google Scholar] [Publisher Link]
- [4] Xiaohu Lu, and Ulf Isacsson, "Laboratory Study on the Low Temperature Physical Hardening of Conventional and Polymer Modified Bitumens," *Construction and Building Materials*, vol. 14, no. 2, pp. 79-88, 2000. [CrossRef] [Google Scholar] [Publisher Link]
- [5] Mahmoud Ameri, and Danial Nasr, "Properties of Asphalt Modified with Devulcanized Polyethylene Terephthalate," *Petroleum Science and Technology*, vol. 34, no. 16, pp. 1424-1430, 2016. [CrossRef] [Google Scholar] [Publisher Link]
- [6] A.S. Mukimov et al., "Modern Approach to the Addition of Organomineral Additives to Increase Cement Brand. A Review," *Chemical Review and Letters*, vol. 7, no. 5, pp. 804-815, 2024. [CrossRef] [Google Scholar] [Publisher Link]
- [7] Botir Khaitov et al., "The Efficiency of Silicious Nano Nutrition on Cotton Productivity in Arid Regions," *Frontiers in Sustainable Food Systems*, vol. 8, pp. 1-8, 2024. [CrossRef] [Google Scholar] [Publisher Link]
- [8] Dennyele Alves Gama et al., "Rheological Studies of Asphalt Modified with Elastomeric Polymer," *Construction and Building Materials*, vol. 106, pp. 290-295, 2016. [CrossRef] [Google Scholar] [Publisher Link]
- [9] Martin Jasso et al., "Rheology of Conventional Asphalt Modified with SBS, Elvaloy and Polyphosphoric Acid," *Fuel Processing Technology*, vol. 140, pp. 172-179, 2015. [CrossRef] [Google Scholar] [Publisher Link]
- [10] Giovanni Polacco et al., "A Review of the Fundamentals of Polymer-Modified Asphalts: Asphalt/Polymer Interactions and Principles of Compatibility," *Advances in Colloid and Interface Science*, vol. 224, pp. 72-112, 2015. [CrossRef] [Google Scholar] [Publisher Link]
- [11] Dennyele A. Gama et al., "Optimizing the Use of Reactive Terpolymer, Polyphosphoric Acid and High-Density Polyethylene to Achieve Asphalt Binders with Superior Performance," *Construction and Building Materials*, vol. 169, pp. 522-529, 2018. [CrossRef] [Google Scholar] [Publisher Link]
- [12] Khankelov Tavbay et al., "Bases of the Method of Physical Modeling of the Process of Crushing of Municipal Solid Waste," *Journal of Applied Engineering Science*, vol. 22, no. 2, pp. 446-457, 2024. [CrossRef] [Google Scholar] [Publisher Link]
- [13] S.B. Mammadli et al., "Synthesis of an Optically Transparent Copolymer on the Basis of N-Vinyl Carbazole and Styrene," *Chemical Problems*, vol. 20, no. 4, pp. 374-380, 2022. [CrossRef] [Google Scholar] [Publisher Link]
- [14] Duschanova Zaynab Atabayevna et al., "Biocompatibility and Toxicity Assessment of Gold Nanoparticles in Nmri Mice," *Journal of Nanostructures*, vol. 14, no. 3, pp. 789-799, 2024. [CrossRef] [Google Scholar] [Publisher Link]
- [15] A.I. Sadygova, "Synthesis of 1-(P-Vinylphenyl)-2-Diethylaminomethylcyclopropane and Its Radical Copolymerization with Methyl Methacrylate," *Chemical Problems*, vol. 19, no. 3, pp. 173-178, 2021. [CrossRef] [Google Scholar] [Publisher Link]
- [16] Yulchieva Marguba Gafurjanovna et al., "Studying Synthesis of a Chelate-Forming Sorbent Based on Urea-Formaldehyde and Diphenylcarbazone," *Indian Journal of Chemistry*, vol. 63, no. 6, pp. 579-585, 2024. [CrossRef] [Google Scholar] [Publisher Link]
- [17] Mokhichekhra Shaymardanova et al. "Studying of the Process of Obtaining Monocalcium Phosphate Based on Extraction Phosphoric Acid from Phosphorites of Central Kyzylkum," *Baghdad Science Journal*, vol. 22, no. 12, pp. 756-775, 2024. [CrossRef] [Google Scholar] [Publisher Link]
- [18] Kh.S. Beknazarov et al., "The Inhibition of the Corrosion of Carbon Steel by Oligomeric Corrosion Inhibitors in Different Media," *International Polymer Science and Technology*, vol. 42, no. 4, pp. 33-37, 2018. [CrossRef] [Google Scholar] [Publisher Link]

- [19] A.A. Ahatov et al., "A Synthesis, Crystal Structure and Properties of Tris(Benzene-1.2-Diamine-N,N')-Cadmium Naphthalene-1.5-Disulfonate Trihydrate Complex Compound," *Indian Journal of Chemistry*, vol. 63, no. 10, pp. 1036-1043, 2024. [CrossRef] [Google Scholar] [Publisher Link]
- [20] Todjiyev Nasiriddinovich Jamoliddin et al., "Spectrophotometric Determination of Microconcentrations of Zinc(II) and Copper(II) in Water and Industrial Alloys Using a New Chromogenic Reagent [4-Amino-5-hydroxy-6-[(5-methyl-2-pyridyl)azo]-3-sulfo-1-naphthyl]sulfonyloxysodium," *Chemical Review and Letters*, vol. 7, no. 3, pp. 388-403, 2024. [Google Scholar] [Publisher Link]
- [21] Kh. Alimnazarov Bekmurod et al., "Synthesis, Crystal Structure and Hirshfeld Surface Analysis of Tetra- (2,4-Dichlorophenoxy acetate)-Cadmium (II) Ethylendiammine 0.6H₂O," *Chemical Data Collections*, vol. 34, 2021. [CrossRef] [Google Scholar] [Publisher Link]
- [22] Gulnoza Djakhangirova et al., "Control of Microbiological Contamination and Content of Cations in Wastewater of Grain Processing Enterprises in Uzbekistan," 5th International Conference on Energetics, Civil and Agricultural Engineering, E3S Web of Conferences, vol. 497, pp. 1-7, 2024. [CrossRef] [Google Scholar] [Publisher Link]